

NuPATCH – Wet

Joint Patching Compound

DESCRIPTION

NuPATCH Wet is an acrylic based patching compound.

Supplied in a water dispersible paste it exhibits minimal shrinkage on drying and good adhesion to clean masonry substrates.

SURFACE PREP. & TEMPERATURES

Surface

- The surface to which this product is applied to should be clean, dry, stable, dirt and dust free, and able to receive a coating.

Temperatures

- During application, the temperature of the substrate should not be below 10°C or over 35°C.
- Protect freshly applied render from high wind, freezing, frost and temperatures below 10° for 48 hours after application.
- The rendered surface should also be protected from rain for up to 24 hours after application.

APPLICATION

Care should be taken to ensure that the product is thoroughly mixed, using a Mixing Drill in an appropriate vessel. Add 10% Cement for all exterior applications.

Mixing

- A Small amount of water can be added to improve troweling properties and floating
- 5% to 10% cement may be added to speed up cure, however; this will slightly reduce flexibility.

Embedding Mesh for Joints

- Do not force the mesh into the render, it should be just below the surface

CLEAN UP

Product should be cleaned from all tools and equipment with clean water immediately after use.

STORAGE

Product should be stored under cover, out of direct sunlight and avoiding extreme temperature changes. Under normal storage conditions (5 - 35°C, away from extremes) sealed, unopened containers of this material would have a shelf life of 6 months from the date of manufacture. If stored for longer than 6 months, product must be rechecked for suitability in the intended application.

PACKAGING

4Ltr PVC Pail

15Ltr PVC Pail

DRYING & CURING

Drying and curing of the product is affected by porosity of the surface/substrate, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide.

- Touch Dry - Approximately 2 hours
- Recoat - Minimum 24 hours
- Thoroughly Dry - Approximately 7 days (Depending on thickness, substrate absorption & climatic conditions)

GRADES

- FINE
- COARSE

RECOMMENDED SUBSTRATES

NuPATCH is recommended for use over the following substrates;

- Fibre Cement Sheet (FCS)
- James Hardie D3 ComTex Panel
- Painted/Glazed Brickwork

Please contact our office on **03 9544 8666** or visit our website **www.nutex.com.au** for substrate specifications.

HEALTH & SAFETY

Please consult the **Material Safety Data Sheet** and read the product packaging carefully before use. Material Safety Data Sheets are available by phoning **03 9544 8666**.

Conditions of Use and Disclaimer

The information contained in this Product Data Sheet is given in good faith based upon our current knowledge and does not imply warranty, express or implied. The information is provided and the product is sold on the basis that the product is used for its intended purpose and is used in a proper workmanlike manner in accordance with the instructions of the Product Data Sheet in suitable and safe working conditions. Under no circumstances will the Company be liable for loss, consequential or otherwise, arising from the use of the product.

Whilst NuTex Coatings takes every care to ensure that any impurities in the Product are eliminated at the time of manufacture, components of the product are natural materials including sands or mineral earths which may occasionally result in minor visual blemishes, NuTex Coatings shall not be liable for any such blemishes.