

Preparation and Coating Specification (SS032-01)

Substrate: Masonry Brickwork

Render Finish: Romano Render

Step 1 – Basecoat



Apply a coat of NuREND Basecoat and immediately finish with a straight edge or float. Work the area until it is flat and even.

Step 2 - Basecoat



Allow the first coat to dry, apply a second coat of NuREND Basecoat. To achieve a flat surface finish, we recommend using a diamond float.

Step 3 – Romano/Dado Bond



This product is applied using a roller and brush. Commencing from the top of the working area down to the bottom. We recommend that brush & roll at the same time to avoid picture framing.

Step 4+5 – Romano Render



Apply Nutex Romano evenly (at approximately 1-2mm thick) with a steel trowel, float the surface. Then apply another skim coat whilst the first coat still has moisture, float the surface until smooth then finish with a sponge.
Use a sponge float to finish rubbing in a circular motion. To minimize the appearance of joint lines always finish a complete wall in one application.

Step 6 – Silicon Sealer (Optional)



This product is spray applied. Commencing from the top of the working area down to the bottom. We recommend that 2 coats be applied wet on wet. Allow the first coat to absorb then apply a second coat before the first coat dries. Only coat an area of size that can be recoated before the first coat dries and this will depend on the prevailing weather conditions (wind, temperature and humidity).



CEMENT BASED PRODUCTS	DATA SHT No.	COVERAGE (ONE COAT)	OTHER
NuREND PLUS Basecoat	PDS101-01	5-7 m ²	Thickness of 2-3mm-Per Coat (no less 5mm in total)
Romano Render	PDS203-01	16 m ²	Thickness of 1-2mm-Per Coat
ACRYLIC BASED PRODUCTS			
Romano/Dado Bond	PDS205-01	15-20 m ²	24hrs Prior to Romano Render
Silicon Sealer	PDS204-01	10-12 m ²	

BOND

24 hours before applying the ROMANO Render, apply a coat of ROMANO BOND. This will ensure good adhesion of the render to the substrate as well as assisting in suction uniformity and prevent premature drying (burning).

ROMANO BOND must be applied before using NuTex ROMANO RENDER.

SUBSTRATE

Ensure the substrate has been installed in accordance with the Manufacturer's guidelines and in accordance with correct building practices, paying particular attention to the positioning of control joints. The success and Integrity of the coating system is dependent on the quality and installation of the substrate.

All Building Codes must be followed for the frame and panel fixing, and be in strict accordance with the Manufacturer's guidelines. It is the responsibility of the Builder/Project Manager to ensure that the Substrate is installed in accordance with Manufacturer's guidelines, project specific engineering specification and relevant building codes prior to commencement of any coatings applications.

SUBSTRATE PREPARATION

The surface of the substrate is to be clean, dry, stable, dirt, dust free and be ready for the first coat to be applied. During application, the temperature of the substrate should not be below 5°C or over 35°C. To avoid high surface temperatures, it is advised to shade the area during the period of application.

IMPORTANCE OF THOROUGH DRYING

Check the table of products (on page 1) carefully to make sure that any acrylic materials being applied over cement based dry powders have had adequate drying time (min. 10 days). The dry powders in our range contain cement and could take up to 28 days to be fully cured. It is the responsibility of the builder and/or contractor to ensure that each surface is thoroughly dry before the acrylic coat is applied.

NuTex Coatings recommend that professional contractors use a moisture meter to determine the degree of dryness. We consider dry conditions (suitable dry) to be consistent with readings of less than 12%. Should a coating be applied on a substrate or surface that has not sufficiently dried, a white bleaching, blistering and/or cracking on the surface may occur in the weeks after application as moisture evaporates out of the system.

WARRANTY

When this particular substrate finishing system is applied as above with all the nominated products, as described in this document, NuTex Coatings will provide a material only replacement warranty caused by any defect in manufacture of its products.

NuTex Coatings provides a seven year warranty for defective product only (product replacement only) against this substrate system, providing the components are of the quality specified and are applied strictly according to the guidelines laid down in this Manual. This manual must be read and understood before applying NuTex products onto this particular substrate.

NuTex Coatings cannot be held responsible, and hence no warranty applies, if the system or its components are not applied according to the guidelines.

As advised above, insufficient or inadequate construction of expansion joints could lead to cracking of the system. Placing of control/expansion joints is the responsibility of the Builder/Engineer/Architect.

Nutex Coatings provide important framework and information platforms within the NUTEX COATINGS Render Finishing system guidelines. Failure to follow our specifications may result in system failure and loss of warranty.

Minimum Requirements: (to commence potential failure investigation)

- Application Dates
- Product Batch Numbers
- Quantities must be recorded and supplied as a minimum to commence potential product failure investigation.

LIMITATIONS

The liability of Nutex Coatings Pty Ltd for any loss, damage or other expenses (whether incurred directly or indirectly) in connection with use of this system is limited to;

- NuTex Coatings renders / textures composition recommendation, including but not limited to, prevailing weather conditions and Protection of finished work.
- Nutex Coatings provides no warranty, expressed or implied, against damage due to movement of the substrate or structure.

Whilst NuTex Coatings takes every care to ensure that any impurities in the Product are eliminated at the time of manufacture, components of the product are natural materials including sands or mineral earths which may occasionally result in minor visual blemishes, NuTex Coatings shall not be liable for any such blemishes.

DISCLAIMER

The information and recommendations contained herein are based on tests and data believed to be reliable and are issued for your guidance. However we cannot accept any responsibility for the results as the use and application of the product is beyond our control. Whilst every effort has been made to ensure that the information in this document is correct at the time of printing, Nutex Coatings Pty Ltd reserves the right to change the specifications of all products referred to in this document.

Document Number & Location	ReadyNAS/Technical/SpecSheets/SS032-01
Document Title	NUTEX COATINGS Romano Render System for Masonry Brickwork
Document Author	Kellie Gebing – Mar 2021